Autex Acoustics <sup>®</sup>	3D Tiles	Data Sheet
Product overview	3D Tiles are lightweight, sculptur interior wall application. Made fro are moulded to form abstract, thr provide acoustic absorption acro	om 100% polyester fibre, 3D Tiles
Sustainable material	<ul> <li>Carbon neutral product</li> <li>Zero carbon manufacturing</li> <li>Recycled content <ul> <li>&gt;55% recycled material</li> </ul> </li> </ul>	<ul> <li>Low VOC and CDPH compliant <ul> <li>&lt;0.0035 mg/m<sup>3</sup> (7 days)</li> </ul> </li> <li>Zero waste manufacturing initiative</li> <li>Sustainable supply chain and anti-modern slavery</li> </ul>
Environmental certifications	<ul> <li>EPD – compliant with ISO 14025 and EN 15804</li> <li>Declare – Red List free (third party verified)</li> </ul>	<ul> <li>ISO 14001 Certified Environmental Management</li> <li>Health Product Declaration</li> <li>CDPH Standard</li> </ul>
Certifying your green building		VELL, LEED, Green Star, and BREEAM building tion for your project. For support and guidance
Specification	Wall treatment shall be 3D Tiles made from thermally moulded, needle punched, felted polyester material containing not less than 55% recycled material as manufactured by Autex www.autexglobal.com Tile (S-5), colour (), sound absorption Class C, NRC 0.75 – if backed with Autex AAB: Class A, NRC 0.90.	Fire rating ISO 9705: Classification: Group 1-S, EN13501-1:2007+A1:2009: B - s1, d2. Tiles to be supplied with 1 standard tile clip per tile. Install as per 3D Tile Install Instructions.



# **Product specifications**

Product name Composition

3D Tiles S-5.26, S-5.28, S-5.32, S-5.34, S-5.50, S-5.53 100% polyester fibre (PET)

#### Installation

Install as per Autex Acoustics recommendations. Install instructions are included in each pack or available on the website.

S-5.26	S-5.28	S-5.32	S-5.34	S-5.50	S-5.53
575 mm x 575 mm	575 mm x 575 mm	575 mm x 575 mm	575 mm x 575 mm	288 mm x 575 mm	575 mm x 575 mm
(+-0.5 mm) (+-0.5 mm)	(+-0.5 mm) (+-0.5 mm)	(+-0.5 mm) (+-0.5 mm)	(+-0.5 mm) (+-0.5 mm)	(+-0.5mm) (+-0.5mm)	(+-0.5 mm) (+-0.5 mm)
80 mm	58 mm	50 mm	58 mm	58 mm	60 mm
(+-0.5 mm)	(+-0.5 mm)	(+-0.5 mm)	(+-0.5 mm)	(+-0.5 mm)	(+-0.5 mm)
1680 gsm	1680 gsm	1680 gsm	1680 gsm	1680 gsm	1680 gsm
	575 mm x 575 mm (+-0.5 mm) (+-0.5 mm) 80 mm (+-0.5 mm)	575 mm x 575 mm     575 mm x 575 mm       (+-0.5 mm) (+-0.5 mm)     (+-0.5 mm) (+-0.5 mm)       80 mm     58 mm       (+-0.5 mm)     (+-0.5 mm)	575 mm x 575 mm       575 mm x 575 mm       575 mm x 575 mm         (+-0.5 mm) (+-0.5 mm)       (+-0.5 mm) (+-0.5 mm)         80 mm       58 mm       50 mm         (+-0.5 mm)       (+-0.5 mm)       (+-0.5 mm)	575 mm x 575 mm       575 mm x 575 mm       575 mm x 575 mm         575 mm x 575 mm       575 mm x 575 mm         (+-0.5 mm) (+-0.5 mm)       (+-0.5 mm) (+-0.5 mm)         80 mm       58 mm         58 mm       50 mm         (+-0.5 mm)       (+-0.5 mm)         (+-0.5 mm)       (+-0.5 mm)         (+-0.5 mm)       (+-0.5 mm)	575 mm x 575 mm       288 mm x 575 mm         (+-0.5 mm) (+-0.5 mm)       (+-0.5 mm) (+-0.5 mm) (+-0.5 mm)       (+-0.5 mm) (+-0.5 mm) (+-0.5 mm)       (+-0.5 mm) (+-0.5 mm)       (+-0.5 mm) (+-0.5 mm)         80 mm       58 mm       50 mm       58 mm       58 mm       58 mm         (+-0.5 mm)       (+-0.5 mm)       (+-0.5 mm)       (+-0.5 mm)       (+-0.5 mm)

4000 NRC

0.75

0.90

0.80

0.90

# Acoustic performance

Frequency (Hz)

without AAB 35-25)

3D Tiles (with AAB 35-25)

**3D** Tiles

3D Tiles S-5.26, S-5.28, S-5.32, S-5.34, S-5.50 and S-5.53 are specifically designed to reduce and control reverberated noise and echo in building interiors. To increase acoustic performance, use Autex AAB 35-25 polyester acoustic insulation as an infill. Refer to www.autexglobal.com.

250

0.45

0.60

500

0.65

0.95

1000

0.90

1.05

2000

0.90


1.00

125

0.15

0.25

Absorption Coefficient According ISO 354 University of Auckland Test Report Number
3D Tiles without AAB 35-25 - Test No. T1012-3
3D Tiles with AAB 35-25 - Test No. T1012-5



# The graph above presents third octave sound absorption coefficients in accordance with ISO 354 measurement of sound absorption in a reverberation room. The table below presents the practical sound absorption coefficients in accordance with ISO 11654. The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centered on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz and rounded to the nearest 0.05.

# **Product specifications**

Product name Composition	3D Tiles S-5.37, S-5.46 100% polyester fibre (PET)				
Product name	S-5.37	S-5.46			
Tile dimensions	575 mm x 575 mm	498 mm x 575 mm			
Tile tolerance	(+-0.5 mm) (+-0.5 mm)	(+-0.5 mm) (+-0.5 mm)			
Depth	140 mm	120 mm			
Depth tolerance	(+-0.5 mm)	(+-0.5 mm)			
Weight	1680 gsm	1680 gsm			

#### Installation

Install as per Autex Acoustics recommendations. Install instructions are included in each pack or available on the website.




### Acoustic performance

3D Tiles S-5.37 and S-5.46 are specifically designed to reduce and control reverberated noise and echo in building interiors.

	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
•	3D Tiles S-5.37, S-5.46	0.15	0.65	0.60	0.70	0.75	0.70	0.65

The graph above presents third octave sound absorption coefficients in accordance with ISO 354 measurement of sound absorption in a reverberation room. The table below presents the practical sound absorption coefficients in accordance with ISO 11654. The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centered on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz and rounded to the nearest 0.05.

Absorption Coefficient According ISO 354 University of Auckland Test Report Number



# Product specifications

#### Fire ratings

3D Tiles is a product made from Workstation as the base material. Workstation has been evaluated using the following test methods:

#### ISO 9705: 1993

Classification: Group 1-S Smoke production rate: <5.0m2/s As required by NZBC C/VM2

#### AS ISO 9705 - 2003

Classification: Group 1 (SMOGRArc): <100m2/s2 Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637.1:2015 as required by BCA Specification C1.10-4 ER 4055

#### EN13501-1:2007+A1:2009

(6mm Workstation) B - s1, d2 Report WF 336913

### ASTM E84 - 14

(12mm Workstation) Class A, FS:0 - SD:10 Report RJ3297

#### Water vapour sorption

ASTM C1104 / C1104M-13a Test conditions: 49°C, 95%RH Water vapour absorbed and adsorped after 4 days: 0.4% by weight.

# Microbial resistance

ASTM G21-15 Growth rating: 0 (No growth) 3D Tiles do not promote the growth of moulds and mildew.

# Colour fastness to light

3D Tiles are suitable for indoor use only.

Lightfastness is dependent on use and exposure. 3D Tiles have been evaluated to the following standard: ISO 105-B02:2014 Rating: 6 (Highest = 7)

# Colour fastness to rubbing

ISO 105-X12:2016 Dry rating: 4-5 (Highest = 5) Wet rating: 4-5 (Highest = 5)

#### Pattern repeat

Non-woven. No pattern repeat, but the product has a directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

#### Fabric care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and using excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed. Blot with a clean, dry cloth after each application of the solution.

Custom printed 3D Tiles require the services of a specialist cleaning company. Refer to the 3D Tiles Care and Maintenance Guide for more information.

#### Service

For further information about 3D Tiles or any other Autex Acoustics product, please contact your account manager or visit our website.



# Light reflectance values by colour

3D Tiles are suitable for indoor use only. LRVs were measured in accordance with BS 8493:2008+A1:2010

Beehive30Blazing Red8Cavalier10Empire3Falling Water32	
Cavalier 10 Empire 3	
Empire 3	
· · · · · · · · · · · · · · · · · · ·	
Falling Water 32	
0	
Flatiron 23	
Gherkin 5	

Muralla	7
Petronas	1
Pinnacle	2
Porcelain	22
Savoye	44
Simba	18
Tree House	2

### New Zealand

702-718 Rosebank Road, Private Bag 19988 Avondale 1746, Auckland T 0800 428 839 T +64 9 828 9179

#### www.autexacoustics.co.nz

# Australia 285 Swan Street, Richmond, VIC 3121 T 1800 678 160 T +61 3 9450 6700 www.autexacoustics.com.au

#### United Kingdom

Unit J4, Lowfields Way, Lowfields Business Park, Elland, West Yorkshire HX5 9DA T +44 0 142 241 8899 www.autexacoustics.co.uk

# United States

1630 Dan Kipper Drive, Riverside, CA 92507 T +1 424 203 1813 www.autexacoustics.com

Autex is an ISO certified organisation encompassing Quality (ISO 9001), Environmental (ISO 14001), and Health and Safety (ISO 45001). Brand names and logos are registered or unregistered trademarks owned or used under license by Autex Industries Limited or other members of the Autex Group. © Copyright 2023 Autex Industries Ltd. All rights reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.